




PCS Fiber

Material: Plastic Clad Silica (PCS)

Characteristics: High OH. Performs good in visible spectrum. Economic alternative to Fused Doped Silica.

Specifications:	Numerical Aperture NA:	Short Lengths (<2 M) 0.40 Long Lengths (>40 M) 0.30
	Acceptance angle:	Short 47° Long 35°
	Fiber diameter (μm):	275
	Bundle length:	Quoted

Spectral Transmission for 1 M Bundle, Fiber Type PCS High OH



PCS Fiber

Material: Plastic Clad Silica (PCS)

Characteristics: Low OH. Performs good across UV, visible, and IR spectrum.
Economic alternative to Fused Dope Silica.

Specifications:

Numerical Aperture NA:	Short Lengths (<2 M) 0.40
	Long Lengths (>40 M) 0.30
Acceptance angle:	Short 47°
	Long 35°
Fiber diameter (μm):	275
Bundle length:	Quoted

TECHNICAL SPECIFICATIONS

Spectral Transmission for 1 M Bundle, Fiber Type PCS Low OH

